

Rec'd PCT/PTO 29 APR 2005  
10/533363

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
27 May 2004 (27.05.2004)

PCT

(10) International Publication Number  
**WO 2004/044345 A2**

(51) International Patent Classification<sup>7</sup>:

**E04F**

(81) Designated States (*national*): AT, AU, CA, CH, DE, DK, GB, JP, SE, US.

(21) International Application Number:

PCT/US2003/032595

(84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

(22) International Filing Date: 15 October 2003 (15.10.2003)

(25) Filing Language:

English

**Declaration under Rule 4.17:**

— of inventorship (Rule 4.17(iv)) for US only

(26) Publication Language:

English

**Published:**

— without international search report and to be republished upon receipt of that report

(30) Priority Data:

60/424,198

5 November 2002 (05.11.2002) US

(71) Applicant and

(72) Inventor: PAUSE, Barbara [DE/US]; 7161 Christopher Court, Longmont, CO 80503 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: WALL COVERING ASSEMBLY WITH THERMO-REGULATING PROPERTIES

(57) Abstract: A wall covering assembly comprising a front layer of a vinyl coated fabric or paper, a rear ceramic layer, and an intermediate layer made of an acrylic compound containing finely divided phase change material such as crystalline acryl hydrocarbons or salt hydrates. The wall covering assembly facilitates thermo-regulation due to latent heat absorption and latent heat release in the phase transition range of the phase change material, which enhances the thermal comfort of rooms and leads to energy savings.

WO 2004/044345 A2

## TITLE OF THE INVENTION:

WALL COVERING ASSEMBLY WITH THERMO-REGULATING PROPERTIES

INVENTOR: BARBARA PAUSE

## CROSS-REFERENCES TO RELATED APPLICATIONS

This application claims priority of US provisional application Serial No. 60/424,198 filed November 5, 2002 entitled "Wallcovering materials with thermo-regulating properties".

## BACKGROUND OF THE INVENTION

Wall covering materials used in homes, hotels or office buildings mainly fulfill a decoration purpose. Wall covering materials are made, for instance, of fabrics or papers with a PVC coating on the front side. The vinyl coating is printed or embossed in order to create different designs and textures. Because of the thinness and high density of a wall covering material it does not contribute to the thermal insulation feature provided by the walls or ceilings the wall covering material is attached to. On the other side, the wall coverings play an important rule in thermal interactions between the walls and the room's interior. The walls release radiant heat into the room and receive radiant heat from the room's interior parts. The wall covering is the part of the wall which is mainly involved in this thermal interaction. The radiant heat absorbed by the wall covering is transported into the walls and the ceiling by conduction. Furthermore, the heat flux from the floor to the ceiling interacts with the wall covering system in form of convective heat. As a result, being at the forefront regarding the heat exchange between the wall and the ceiling and the room interior, the wall covering should be considered for providing a thermo-regulating feature. A thermo-regulating feature supplied by the wall coverings leads to a substantial improvement of the thermal comfort of rooms. Furthermore, a thermo-regulating effect provided by the wall covering system results in a decrease in air-conditioning and heating demands which leads to substantial energy savings as well. A thermo-regulating effect can be provided by the application of phase change material.

Phase change material is a highly-productive thermal storage medium which possesses the ability to change its physical state within a certain temperature range. When the melting temperature is obtained during a heating process, the phase change from the solid to the liquid state occurs. During this melting process, the phase change material absorbs and stores a large amount of latent heat. The temperature of the phase change material remains nearly constant

during the entire process. In a cooling process of the phase change material, the stored heat is released into the environment in a certain temperature range, and a reverse phase change from the liquid to the solid state takes place. During this crystallization process, the temperature of the phase change material also remains constant. The high heat transfer during the melting process and the crystallization process, both without any temperature change, is responsible for the phase change material's appeal as a source of heat storage.

In order to contrast the amount of latent heat absorbed by a phase change material during the actual phase change with the amount of sensible heat absorbed in an ordinary heating process, the ice-water phase change process will be used. When ice melts, it absorbs an amount of latent heat of about 335 J/g. When the water is further heated, it absorbs a sensible heat of only 4 J/g while its temperature rises by one degree C. Therefore, the latent heat absorption during the phase change from ice into water is nearly 100 times higher than the sensible heat absorption during the heating process of water outside the phase change temperature range.

In addition to ice (water), more than 500 natural and synthetic phase change materials are known. These materials differ from one another in their phase change temperature ranges and their latent heat storage capacities.

Currently, only crystalline alkyl hydrocarbon phase change materials having different chain lengths are used for finishing yarns, textiles and foams. Characteristics of these phase change materials are summarized in Table 1.

Table 1: Crystalline alkyl hydrocarbons

| Crystalline alkyl hydrocarbons | Formula                         | Melting temperature, °C | Crystallization temperature, °C | Latent heat storage capacity, J/g |
|--------------------------------|---------------------------------|-------------------------|---------------------------------|-----------------------------------|
| Eicosane                       | C <sub>20</sub> H <sub>42</sub> | 36.1                    | 30.6                            | 247                               |
| Nonadecane                     | C <sub>19</sub> H <sub>40</sub> | 32.1                    | 26.4                            | 222                               |
| Octadecane                     | C <sub>18</sub> H <sub>38</sub> | 28.2                    | 25.4                            | 244                               |
| Heptadecane                    | C <sub>17</sub> H <sub>36</sub> | 21.7                    | 16.5                            | 213                               |

The crystalline alkyl hydrocarbons are either used in technical grades with a purity of approximately 95 % or they are blended with one another in order to cover specific phase change temperature ranges. The crystalline alkyl hydrocarbons are nontoxic, non-corrosive, and non-hygroscopic. The thermal behavior of these phase change materials remains stable under

permanent use. Crystalline alkyl hydrocarbons are byproducts of petroleum refining and, therefore, inexpensive.

Salt hydrates are alloys of inorganic salts and water. The most attractive properties of salt hydrates are the comparatively high latent heat values, the high thermal conductivities and the small volume change during melting. Salt hydrates often show an incongruent melting behaviour which results in a lack in reversible melting and freezing making them unsuitable for permanent use. Salt hydrates with reversible melting and freezing characteristics are summarized in Table 2.

Table 2: Salt hydrates

| Salt hydrates                | Melting temperature, °C | Latent heat storage capacity, J/g |
|------------------------------|-------------------------|-----------------------------------|
| Calcium Chloride Hexahydrate | 29.4                    | 170                               |
| Lithium Nitrate Trihydrate   | 29.9                    | 236                               |
| Sodium Sulfate Decahydrate   | 32.4                    | 253                               |

In the present applications of the phase change material technology in textiles, only crystalline alkyl hydrocarbon are used which are microencapsulated, i.e., contained in small micro-spheres with diameters between 1 micron and 30 microns. These microcapsules with enclosed phase change material are applied to a textile matrix by incorporating them into acrylic fibers and polyurethane foams or by coating them onto textile surfaces.

U.S. Patent 4,756,958 reports a fiber with integral micro-spheres filled with phase change material which has enhanced thermal properties at predetermined temperatures.

U.S. Patent 5,366,801 describes a coating where micro-spheres filled with phase change material are incorporated into a coating compound which is then topically applied to fabric in order to enhance the thermal characteristics thereof.

U.S. Patent 5,637,389 reports an insulating foam with improved thermal performance, wherein micro-spheres filled with phase change material are embedded.

The micro-encapsulation process of crystalline alkyl hydrocarbon phase change materials is a very time-consuming and complicated chemical process running over several stages making the microcapsules with enclosed phase change material very expensive.

There are several thermal effects which can be obtained by a phase change material application in a certain product, such as:

- A cooling effect, caused by heat absorption of the phase change material.
- A heating effect, caused by heat emission of the phase change material.
- A thermo-regulating effect, resulting from either heat absorption or heat emission of the phase change material.

The efficiency of each of these effects is determined by the latent heat storage capacity of the phase change material, the phase change temperature range and the structure of the carrier system.

The total latent heat storage capacity of the phase change material in a certain product depends on the phase change material's specific latent heat storage capacity and its quantity. In order to obtain a successful phase change material application, the phase change temperature range and the application temperature range need to correspond.

In addition, performance tests carried out on textiles with phase change material have shown that the textile substrate construction also influences the efficiency of the thermal effects obtained by the phase change material. For instance, thin textiles with high densities readily support the heat absorption process.

#### SUMMARY OF THE INVENTION

The invention pertains to a wall covering assembly, which comprises phase change materials such as crystalline alkyl hydrocarbons or salt hydrates as a thermal storage mean. By either absorption or release of large amounts of latent heat without temperature changes, the phase change material adds a thermo-regulating feature to a wall covering system. The design of the newly-invented wall covering assembly allows for a latent heat storage capacity of up to 40kJ/m<sup>2</sup>. Applying the developed wall covering assembly to interior walls and ceilings, a phase change material is required which absorbs latent heat in a temperature range between 25°C and 35°C and releases heat in a temperature range between 15 °C and 25 °C. The use of a wall covering assembly with thermo-regulating properties in rooms of residential or commercial buildings will lead to an enhanced thermal comfort and significant energy savings.

In order to manufacture the invented wall covering assembly, an acrylic coating compound containing finely divided phase change material of up to 60 wt. % is applied onto the

uncoated side of a paper or fabric commonly used in a conventional wall covering system. A second layer coated on top of the acrylic compound layer with phase change material consists of a liquid ceramic compound which provides the required fire resistance, a thermal resistance which minimizes the heat flux into the wall and a protective function against dissolution of the phase change material while in its liquid stage. The character and the decorative function of a common wall covering material is maintained in the invented wall covering assembly.

#### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a graphical representation of the daily development of the room temperature and the average temperature of the floor, the walls and the ceiling of a model room.

FIG. 2 is a sectional view of the invented wall covering assembly with phase change material.

FIG. 3 is a graphical representation of a daily temperature development on walls of a model room equipped with wall coverings with and without phase change material.

FIG. 4 is a graphical representation of a daily temperature development on the ceiling of a model room equipped with wall coverings with and without phase change material.

#### DETAILED DESCRIPTION OF THE INVENTION

The invention pertains to wall covering systems which are made, for instance, out of a vinyl coating on top of a fabric or a paper. The vinyl is then printed and embossed. The wall coverings are attached to the walls or ceilings of rooms inside residential or commercial buildings.

The room temperature normally changes during the day and overnight. During the day, heat caused by solar radiation penetrates through the windows into the room leading to an increase in the room temperature. The heat rises to the ceiling and increases mainly the temperature at the upper parts of the walls and at the ceiling. The temperature rise in the upper part of the room leads to an increase of the temperature gradient between the floor and the ceiling. Overnight the heat is released through the windows resulting in a decrease in the room temperature and the temperatures at the ceiling, the walls and the floor. The temperature gradient between the floor and the ceiling is also reduced during the heat release overnight. Test results received for the development of the room temperature and the temperature development on

different locations of a model room (floor, walls and ceiling) during a 24 hour-period are shown in FIG. 1.

A comfortable room temperature ranges between 21 °C and 24 °C. Furthermore, in order to avoid uncomfortable drafts in the room, the vertical temperature gradient between floor and ceiling should not exceed 3 K/m. A vertical temperature gradient of 1 K/m would be most preferable. Based on these data the floor temperature should be in the range between 20 °C and 23 °C. At the ceiling the temperature should remain between 23 °C and 26 °C during the day.

In order to keep the room temperature in the comfort range, especially on hot summer days, the phase change material should mainly be used to absorb excess heat the wall and the ceiling are subjected to. Considering the comfort temperature ranges determined for walls and ceiling, the applied phase change material should absorb heat if temperature on the surface of the walls exceed 25 °C and the ceiling temperature rises above 26 °C. Based on model calculations, the phase change material applied to walls should absorb latent heat in a temperature range between 25 °C and 32°C. A phase change material used in a wall covering assembly attached to the ceiling should absorb latent heat in a temperature range between 26 °C and 35°C. The phase change material selected for both applications should be able to release all the stored latent heat overnight with the reverse heat flux through the windows into the environment. Only in case the stored heat can be released completely overnight, the phase change material can fulfill its heat absorption function during the day. A appropriate temperature range for the release of the latent heat stored in the walls and in the ceiling ranges from 15 °C up to 25 °C.

In order to cover the selected temperature ranges for the latent heat absorption, paraffin waxes described in Table 1 can be used for the wall covering assembly. Salt hydrates summarized in Table 2 are also suitable for such an application.

The wall covering materials are very thin and flexible. In order to keep these characteristics of the wall covering materials, the amount of phase change material which can be applied to such a system is limited. The limitations in the phase change material quantity demand that technical grade paraffin waxes and salt hydrates with latent heat storage capacities of at least 180 J/g are used in wall covering systems.

In order to obtain a sufficient latent heat storage capacity in the wall covering material the use of microencapsulated phase change material should be avoided. The micro-encapsulation procedure of the phase change material reduces the latent heat storage capacity by about 40%. In

order to maximize the latent heat storage capacity of the wall covering assembly, pure phase change material has been applied directly to an acrylic coating compound. The acrylic coating compound is liquid at room temperature. In order to obtain an even distribution of the crystalline alkyl hydrocarbons or the salt hydrates throughout the acrylic coating compound, the phase change material also have to be liquid for mixing them into the acrylic substrate. Because the crystalline alkyl hydrocarbons and the salt hydrates which melt in the selected application temperature range are solid at the processing room temperature, they need to be melted first. After the selected phase change material is completely melted it is carefully mixed into the acrylic coating compound. The acrylic coating compound with incorporated phase change material (2) is then applied to the uncoated side of a paper or fabric commonly used in conventional wall covering systems as a first additional layer. In addition to the phase change material, the acrylic coating compound may also contain flame-retarding additives which are mixed therein together with the phase change material. In the next step, a second layer of a liquid ceramic compound (3) is coated on top of the layer comprising the acrylic coating compound with phase change material in order to enhance the wall covering's fire-resistance and avoid the dissolution of the PCM while in a liquid stage. The rear ceramic layer is abrasion resistant and possesses a plain surface. A sectional view of the invented wall covering assembly is shown in FIG. 2.

Preferably, phase change material has been applied to the acrylic coating compound in a quantity of about 50 wt.%. The total phase change material quantity of  $130 \text{ g/m}^2$  in the acrylic coating compound leads to a latent heat storage capacity of approximately  $25 \text{ kJ/m}^2$  to  $35 \text{ kJ/m}^2$ . By applying the same quantity of microencapsulated phase change material, a latent heat storage capacity of only  $16 \text{ kJ/m}^2$  could be obtained which is not sufficient for the intended room application. At least a latent heat capacity of  $25 \text{ kJ/m}^2$  is necessary to obtain long-lasting thermal effects in room applications. Technical data of wall covering materials with and without phase change material are summarized in Table 3.

The test data indicate that the thin wall covering material possesses only a low thermal resistance which ensures a sufficient heat transfer into the layer which contains the phase change material and away from it. The application of  $130 \text{ g/m}^2$  pure phase change material incorporated into the wall covering in an acrylic coating compound increases the weight of the wall covering material by about 70%. The addition of a first layer to the existing wall covering material



(acrylic coating compound with incorporated phase change material) doubles the thickness of wall covering material. However, the increase in thermal resistance totals only 40%.

Table 3: Technical data of wall covering materials with and without phase change material

|  | Weight per unit area<br>in g/m <sup>2</sup> | Thickness<br>in mm | Thermal resistance<br>in m <sup>2</sup> K/W | Latent heat storage capacity<br>in kJ/m <sup>2</sup> |
|--|---|--------------------|---|--|
| Wall covering without phase change material  | 365   | 0.45               | 0.0061                                      | -  |
| Wall covering with about 130 g/m <sup>2</sup> phase change material in an acrylic coating compound                                   | 625   | 1.02               | 0.0085                                      | 27.3   |
| Wall covering with about 130 g/m <sup>2</sup> phase change material in an acrylic coating compound and an additional ceramic coating | 745   | 1.22               | 0.0119                                      | 27.3   |

The addition of the second layer made of a ceramic compound adds about 120g/m<sup>2</sup> in weight to the wall covering assembly. This ceramic layer possesses only a thickness of 0.2mm. Despite its relative thinness, the ceramic compound layer possesses a comparatively high thermal resistance which reduces the heat flux into the walls and the ceiling substantially. The thermal resistance of the final wall covering configuration with phase change material is about twice the thermal resistance of the wall covering material without phase change material.

After adding the two coating layers to an existing wall covering material the invented wall covering assembly is still a flat structure which can be applied to a wall in the manner of wallpaper. The wall covering assembly is thin and flexible which makes it possible to transport and store the material in form of rolls. By keeping the original fabric or paper with the vinyl coating on the front face of the assembly the decorative design function of the wall covering is maintained.

The wall covering material with phase change material has been tested in a model room. Some test results are shown in FIG. 3 and FIG. 4. The test results indicate that the temperature increase on the walls and the ceiling, for instance, during a hot summer day could be delayed and, therefore, reduced by the heat absorption of the phase change material incorporated in the wall covering assembly. On the other side, the phase change material has been recharged

overnight by releasing the stored heat. The thermal effect provided by the phase change material contained in the wall covering assembly has been proven to be durable in more than 1000 thermo-cycles. The phase change material application in wall covering materials will lead to a better thermal comfort inside buildings and to substantial energy savings.

**CLAIMS**

What is claimed is:

- A wall covering assembly for covering a structure, such as a wall or a ceiling, comprising:
- a cover layer consisting of a fabric or paper where a vinyl coating is provided to one side and that this side confronts the viewer during use;
  - an intermediate layer made of an acrylic coating compound containing finely divided phase change material;
  - and a rear layer made of a liquid ceramic compound facing the wall during use.
2. A wall covering assembly according to claim 1, wherein the acrylic coating compound comprises phase change material in a quantity of up to 60 wt.%.
  3. A wall covering assembly according to claim 1, wherein the intermediate layer made of an acrylic coating compound contains flame-retarding additives in addition to the phase change material.
  4. A wall covering assembly according to claim 1, wherein the acrylic coating compound with the incorporated phase change material is coated onto the side of the fabric or paper where no vinyl coating is applied.
  5. A wall covering assembly according to claim 1, wherein the ceramic layer is topically applied to the acrylic compound layer with incorporated phase change material by coating.
  6. A wall covering assembly according to claim 1, wherein the phase change material is a crystalline alkyl hydrocarbon.
  7. A wall covering assembly according to claim 1, wherein the phase change material is a salt hydrate.
  8. A wall covering assembly according to claim 1, wherein the phase change materials have melting points in the range between 20 °C and 40 °C.
  9. A wall covering assembly according to claim 1, wherein the phase change materials have melting points in the range between 25 °C and 35 °C.
  10. A wall covering assembly according to claim 1, possessing a latent heat storage capacity between 20 kJ/m<sup>2</sup> and 40 kJ/m<sup>2</sup>.

## DRAWINGS

## APPLICATION:

## WALL COVERING ASSEMBLY WITH THERMO-REGULATING PROPERTIES

## PAGE 1:




FIG. 1




FIG. 2

## DRAWINGS

## APPLICATION:

## WALL COVERING ASSEMBLY WITH THERMO-REGULATING PROPERTIES

## PAGE 2:




FIG. 3




FIG. 4

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
27 May 2004 (27.05.2004)

PCT

(10) International Publication Number  
**WO 2004/044345 A3**

- 
- (51) International Patent Classification<sup>7</sup>: **B32B 27/12**, (81) Designated States (*national*): AT, AU, CA, CH, DE, DK, GB, JP, SE, US.  
27/04
- (21) International Application Number: PCT/US2003/032595 (84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).
- (22) International Filing Date: 15 October 2003 (15.10.2003) Declaration under Rule 4.17:  
— of inventorship (Rule 4.17(iv)) for US only
- (25) Filing Language: English Published:  
— with international search report
- (26) Publication Language: English
- (30) Priority Data: 60/424,198 5 November 2002 (05.11.2002) US (88) Date of publication of the international search report:  
12 August 2004
- (71) Applicant and (72) Inventor: PAUSE, Barbara [DE/US]; 7161 Christopher Court, Longmont, CO 80503 (US). For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.
- 

(54) Title: WALL COVERING ASSEMBLY WITH THERMO-REGULATING PROPERTIES

(57) Abstract: A wall covering assembly comprising a front layer of a vinyl coated fabric or paper, a rear ceramic layer, and an intermediate layer made of an acrylic compound containing finely divided phase change material such as crystalline acryl hydrocarbons or salt hydrates. The wall covering assembly facilitates thermo-regulation due to latent heat absorption and latent heat release in the phase transition range of the phase change material, which enhances the thermal comfort of rooms and leads to energy savings.

WO 2004/044345 A3

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/US03/32595

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : B32B 27/12, 27/04

US CL : 442/59, 64, 65, 66, 67, 68, 70, 71, 72, 74, 79, 85

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 442/59, 64, 65, 66, 67, 68, 70, 71, 72, 74, 79, 85

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
Please See Continuation Sheet

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category * | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|------------|--|-----------------------|
| Y,P        | US 2003/0054141A1 (WORLEY et al) 20 March 2003 (20.03.2003), see entire document.  | 1-10                  |

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

31 March 2004 (31.03.2004)

Date of mailing of the international search report

07 MAY 2004

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US

Commissioner for Patents

P.O. Box 1450

Alexandria, Virginia 22313-1450

Facsimile No. (703)305-3230

Authorized officer

Lia C Ruddock

Telephone No. 571-272-1200

**INTERNATIONAL SEARCH REPORT**

PCT/US03/32595

**Continuation of B. FIELDS SEARCHED Item 3:**

**WEST**

search terms: fabric, textile, cloth, paper, fibrous, coating, impregnation, vinyl, acrylic, ceramic, compound, composition, phase change, wall, floor, covering, ceiling